

SILICONES and more



Characteristics

Silicone Condensation 20 Starter kit

These Silicones are ideal for making soap Moulds, Candle Moulds, Concrete moulds etc.

Description

The silicone Condensation 20 - A + B is a 2-component (poly-condensation curing) castable molding silicone which cures at room temperature. The silicone has a good fluidity and gives great detail while still remaining strong. Silicone C 20 -A + B are excellently suited for the casting of e.g. cement, plaster, wax, soap, and many other casting materials.

Technical data

Mixing ratio (weight)	[A: B]	100: 2 (1.5 ~ 3)
Pot Life @ 20 ° C	[Min]	60
De-mould time @ 20°C	[Hours]	14
Full strength after	[Days]	3
Hardness	[Shore A]	23-28
Viscosity @ 20 °C	[mPa s]	12.000 +/- 2.000
Tear strength	[Kg/cm ²]	43,2

note: Pot life and de-mould time are highly dependent on the mixing ratio and Humidity! By adding more than 2% silicone B (hardener) or at high humidity, the pot life and de-mould time are shorter.

Processing

The silicone C 20 - A + B can easily be mixed by hand or by machine. Mix the A and B component carefully and in the indicated ratio (preferably 2%, you can add between 1.5-3% B comp)

Example: To 1 kg of A-Comp add preferably 20 grams of B-component. You can vary between 15 grams (1.5%) up to 30 grams (3%). Less or more will inhibit cure or alter the final properties of the rubber.

At 1.5%, the silicone will take longer to harden giving air bubbles more time to escape. with 3% B component the silicone will cure considerably faster. Process the mixture in the pot life and never take more than you can handle within pot-life.

Only de-mould after a complete cure. If you wish to make a mold by using a brush or spatula you need to add a 3rd component (0.6% -2% Thixo C). Thixo C thickens the mixture and makes it possible to set up the silicone against vertical surfaces. Please be aware that the mold in this case must be provided with a support cap. This support cap may consist of gypsum bandages or epoxy support cover or acrylic resin with glass fibre fabric.

Packing

The products are packaged in packs of 1 kg A-component, 20 grams of B-component and 50 grams Thixo. In addition you will receive one wooden spatula, one 50 ml syringe, two pair of gloves, one apron and one mixing cup of 550 ml with cover. For larger packages we ask you to contact us through the site.

Durability

Provided that the silicone is tightly sealed and stored in a cool and frost-free location, the shelf life is at least 1 year.

Safety If you frequently work with the silicone is recommended to use protective gloves and to properly ventilate the area. For safety instructions, always read the safety data sheet.

Starter kit includes

- 1 kg of Silicone C 20 -A
- 20 Grams Silicone C 20 -B
- 50 Grams Silicone Thixo C
- 1 Dosseerspuit
- 1 Apron
- 550 ml Blender + Lid
- Mix Patel
- 2 Pairs of gloves