

ELASTOSIL[®] M 4644 A/B

ELASTOSIL[®]

Room Temperature Curing Silicone Rubber (RTV-2)

Pourable, addition-curing, two-component silicone rubber that vulcanizes at room temperature.

Main application: Vacuum casting for rapid prototyping.



Properties

- good flow
- fast and non-shrink cure at room temperature which can be accelerated considerably by the application of heat
- medium Shore A hardness (approx. 40)
- good transparency of the cured rubber
- high tear strength
- outstanding resistance to casting resins, particularly polyurethanes and epoxies, for very long service life of the molds
- slightly oil-bleeding

Specific features

- Addition-curing
- Excellent mechanical properties
- No shrinkage
- Slightly oil bleeding
- Two-component

Technical data

Properties Uncured

Property	Condition	A	B	Method
Color	-	translucent	colorless	-
Density	23 °C	1.08 g/cm ³	0.97 g/cm ³	-
Viscosity, dynamic after stirring	23 °C	70000 mPa·s	500 mPa·s	ISO 3219

These figures are only intended as a guide and should not be used in preparing specifications.

Catalyzed

Property	Condition	Value	Method
Viscosity, dynamic	23 °C	50000 mPa·s	ISO 3219
Mix ratio ⁽¹⁾	-	10 : 1	A : B
Pot life ⁽²⁾	-	80 min	-
Curing time tack-free	-	12 h	-

⁽¹⁾(pbw)

⁽²⁾at 23 °C, up to 150000 mPa s

These figures are only intended as a guide and should not be used in preparing specifications.

Properties Cured

Vulcanizate after 24 h at 23 °C

Property	Condition	Value	Method
Color	-	translucent	-
Density in water	23 °C	1.07 g/cm ³	ISO 2781
Hardness Shore A	-	40	ISO 868
Tensile strength	-	5.5 N/mm ²	ISO 37
Elongation at break	-	400 %	ISO 37
Linear shrinkage	-	≤ 0.1 %	-
Tear strength	-	> 25 N/mm	ASTM D 624 B

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Prototype Molding

Application details

High-performance silicone mold-making compound which is particularly suitable for reproducing models with undercuts in polyurethane or epoxy resins.

Main field of application: Vacuum casting for rapid prototyping.

Processing

Important note:

The platinum catalyst is in **component A**.

Important:

A and B components may only be used together if they have the same batch number.

Bitte beachten Sie auch unsere Broschüren und Informationsblätter.

Packaging and storage

Storage

The 'Best use before end' date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

Components of the addition-curing grade ELASTOSIL® M 4644 A/B contain only constituents that over many years have proved to be neither toxic nor aggressive. Special handling precautions are therefore not required, i.e., only the general industrial hygiene regulations apply.

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

QR Code ELASTOSIL® M 4644 A/B



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Hanns-Seidel-Platz 4, 81737 Munich, Germany
info@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.