

# ELASTOSIL® M 4630 A/B

RTV-2 SILICONE RUBBER / MOLD MAKING

## Product description

Pourable, addition-curing, two-component silicone rubber that vulcanizes at room temperature.

## Special features

- very good flow
- fast and non-shrink cure at room temperature which can be accelerated considerably by the application of heat
- low Shore A hardness (approx. 28)
- high tear strength
- excellent long-term stability of the mechanical properties of the vulcanizate
- outstanding resistance to concrete

## Application

Due to its outstanding resistance to concrete and superior mechanical properties, ELASTOSIL® M 4630 A/B is ideal for use in molds for making concrete reproductions of models with deep undercuts.

As a low-Shore, addition-curing RTV-2 silicone rubber, which cures without dimensional shrinkage, ELASTOSIL® M 4630 A/B is also extremely suitable for casting all other common reproduction materials, especially casting resins where absolutely accurate copies of models with pronounced undercuts are required.

## Processing

Important:

The platinum catalyst is contained in component B.

Caution:

Only components A and B with the same lot number may be processed together!

Comprehensive instructions are given in our leaflet "ELASTOSIL® - PROCESSING RTV-2 SILICONE RUBBERS".

Detailed information on other mold-making compounds in the ELASTOSIL® M range is contained in our brochure "ELASTOSIL® M. Mold-Making Compounds For Maximum Precision".

## Storage

The 'Best use before end' date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

## Additional information

Please visit our website [www.wacker.com](http://www.wacker.com).

## Safety notes

Components A and B of the addition-curing grade ELASTOSIL® M 4630 A/B contain only constituents that over many years have proved to be neither toxic nor aggressive. Special handling precautions are therefore not required, i.e., only the general industrial hygiene regulations apply.

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

**Product data****Typical general characteristics****Inspection Method****Value****Product data (uncured)****Component A**

Color		light gray
Density at 23 °C		1,14 g/cm <sup>3</sup>
Viscosity at 23 °C, after stirring	ISO 3219	15000 mPa s

**Component B**

Color		white
Density at 23 °C		1,01 g/cm <sup>3</sup>
Viscosity at 23 °C, after stirring	ISO 3219	800 mPa s

**Product data (catalyzed A + B)**

Mix ratio	A : B	10 : 1 pbw
Viscosity at 23 °C	ISO 3219	10000 mPa s
Pot-life at 23 °C (up to 60,000 mPas)		90 min
Cure time, tack-free		12 h

**Product data (cured)**

Color		white
Density at 23 °C in water	ISO 2781	1,13 g/cm <sup>3</sup>
Hardness Shore A	ISO 868	28
Tensile strength	ISO 37	6,50 N/mm <sup>2</sup>
Elongation at break	ISO 37	700 %
Tear strength	ASTM D 624 B	> 30 N/mm
Linear shrinkage		< 0,1 %

Vulcanizate after 24 h at 23 °C

These figures are only intended as a guide and should not be used in preparing specifications.

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.

The management system has been certified according to DIN EN ISO 9001 and DIN EN ISO 14001

WACKER® is a trademark of Wacker Chemie AG. ELASTOSIL® is a trademark of Wacker Chemie AG.

For technical, quality, or product safety questions, please contact:

Wacker Chemie AG  
Hanns-Seidel-Platz 4  
81737 München, Germany  
info.silicones@wacker.com

[www.wacker.com](http://www.wacker.com)